

SACADA Database Code: 48

Topology: pbz (Allotrope with "sp" atoms)

of independent nodes (IN): 1
Transitivity: [1231]
Space Group: P6/mmm
Pearson: cP48
Coordination Number (CN): 2, 3 (1:1)

Year: 1993

Data

Name	Pressure, GPa	Density, g/cm ³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
pbz (SACADA #48)		1.037		1.382	99.8	18.2	3.0	SACADA ¹
Cubic a-Graphyne		1.050	2.31					doi: 10.1016/0379-6779(93)90951-r 

Elasticity tensor (kBar)¹

1143.0563	926.2837	926.2837	0.0000	0.0000	0.0000
926.2837	1143.0563	926.2837	-0.0000	0.0000	-0.0000
926.2837	926.2837	1143.0563	0.0000	0.0000	-0.0000
0.0000	-0.0000	0.0000	256.6694	-0.0000	0.0000
0.0000	0.0000	0.0000	-0.0000	256.6694	0.0000
0.0000	-0.0000	-0.0000	0.0000	0.0000	256.6694

¹ We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ -centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025 \text{ \AA}^{-1}$ is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and 10^{-5} eV $\text{\AA}^{-1}$ for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young’s modulus, and the Poisson’s ratio ν — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker’s hardness H_v has been estimated according to Oganov’s model [9].