

SACADA Database Code: 50

Topology: pbz (Allotrope with "sp" atoms)

of independent nodes (IN): 1
Transitivity: [1231]
Space Group: Pn-3m
Pearson: cP72
Coordination Number (CN): 2, 3 (1:2)

Year: 1993

Data

Name	Pressure, GPa	Density, g/cm³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
pbz (SACADA #50)		.603		1.397	62.7	27.2	3.8	SACADA ¹
Cubic Graphadiyne		0.607						doi: 10.1016/0379-6779(93)90951-r 

Elasticity tensor (kBar)¹

852.2384	515.4565	515.4565	-0.0000	0.0000	0.0000
515.4565	852.2384	515.4565	-0.0000	0.0000	-0.0000
515.4565	515.4565	852.2384	0.0000	0.0000	0.0000
-0.0000	-0.0000	0.0000	376.1323	0.0000	-0.0000
0.0000	0.0000	0.0000	0.0000	376.1323	-0.0000
0.0000	-0.0000	0.0000	-0.0000	-0.0000	376.1323

¹ We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ -centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025 \text{ \AA}^{-1}$ is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and $10^{-5} \text{ eV \AA}^{-1}$ for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young’s modulus, and the Poisson’s ratio ν — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker’s hardness H_v has been estimated according to Oganov's model [9].