

SACADA Database Code: 598

Topology: 4³T174-CA

of independent nodes (IN): 3
Transitivity: [3(10)(10)4]
Space Group: P42/nmc
Pearson: tP48
Coordination Number (CN): 4

Year: 2021

Data

Name	Pressure, GPa	Density, g/cm ³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
4 ³ T174-CA (SACADA #598)		3.187		0.406	373.7	333.0	54.5	SACADA ¹
4 ³ T174-CA								doi: 10.1038/s41524-021-00491-y ↗

Elasticity tensor (kBar)¹

7605.1517	1685.6134	1230.1182	0.0000	-0.0000	0.0000
1685.6134	7605.1517	1230.1182	0.0000	-0.0000	-0.0000
1230.1182	1230.1182	10340.6826	0.0000	0.0000	0.0000
0.0000	0.0000	0.0000	2650.2796	-0.0000	0.0000
-0.0000	0.0000	0.0000	-0.0000	3545.7694	-0.0000
0.0000	-0.0000	0.0000	0.0000	-0.0000	3545.7694

¹ We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ -centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025 \text{ \AA}^{-1}$ is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and 10^{-5} eV $\text{\AA}^{-1}$ for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young’s modulus, and the Poisson’s ratio ν — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker’s hardness H_v has been estimated according to Oganov’s model [9].