

SACADA Database Code: 636

Topology: 4³T194-CA

of independent nodes (IN): 3
Transitivity: [3553]
Space Group: Pcca
Pearson: oP16
Coordination Number (CN): 4

Year: 2023

Data

Name	Pressure, GPa	Density, g/cm ³	Gap, eV	Relative energy, eV/atom	Bulk, GPa	Shear, GPa	Vickers, GPa	Refs
4 ³ T194-CA (SACADA #636)		3.489		0.427	420.5	459.1	85.4	SACADA ¹
4 ³ T194-CA								doi: 10.1107/S205252062300255X ↗

Elasticity tensor (kBar)¹

12657.5868	498.2442	977.6062	0.0000	0.0000	0.0000
498.2442	8986.9202	1845.9520	0.0000	0.0000	-0.0000
977.6062	1845.9520	9751.4357	0.0000	-0.0000	0.0000
0.0000	0.0000	0.0000	4421.7627	0.0000	-0.0000
0.0000	0.0000	-0.0000	0.0000	4264.2055	0.0000
-0.0000	-0.0000	-0.0000	-0.0000	-0.0000	5162.0122

¹ We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) to calculate the total energy and properties of carbon allotropes.

DFT calculations

We apply the density functional theory (DFT) approach by using the Vienna Ab Initio Simulation Package (VASP) package [6] to calculate the total energy of carbon allotropes. The Generalized Gradient Approximation [7] (GGA) for exchange-correlational functional is used everywhere. The energy cutoff set to 600 eV. Fully automatic Γ -centered k-points mesh with a reciprocal-space resolution of $2\pi \times 0.025 \text{ \AA}^{-1}$ is applied. We used tetrahedron method with Blöchl corrections to perform the k-point integration. The convergence thresholds are set at 10^{-6} eV for energy and 10^{-5} eV $\text{\AA}^{-1}$ for ionic forces. Polycrystalline elastic moduli — the bulk modulus, the shear modulus, Young’s modulus, and the Poisson’s ratio ν — have been calculated within the Voigt-Reuss-Hill [8] approximation. The Vicker’s hardness H_v has been estimated according to Oganov’s model [9].